

A1 Garnet Premium

SPECIFICATIONS

GRADE #80

Mineralogy	Guaranteed (%)	Typical (%)
Garnet	Min - 90	92
Chemical Analysis		
Parameters		Typical (%)
SiO₂		36-38%
Al₂O₃		20-23%
Fe₂O₃		31-33%
TiO₂		1-1.5%
CaO		1-1.5%
MgO		6-8%
ZrO₂		Traces
Soluble Chloride		Less than 20 ppm
Sieve Analysis		
Mesh (US)		Retention (%)
+40		0
+50		16
+60		47
+80		25
+100		6
-100		6
Physical Analysis		
Specific Gravity		4.1
Hardness		7.5 - 8.00 (Moh Scale)
Bulk Density		2.40 gm/cm ³
Conductivity		< 10 Micron Siemens/Metre

Note: Garnet is a natural product and as such slight variations in the chemical analysis and size distribution should be expected. Special contracts covering guarantees other than those specified can be negotiated.

Packaging

- 25 kgs. PE bags (max. 1000 kgs/ 1MT.)
- 1000 kgs. In 1MT Jumbo bag.

Maxworth International Pty. Ltd.

Level 1, 76-80 Turnham Avenue, Rosanna Victoria-3084, Australia
Tel: +61 3 9455 4400 | Fax: +61 3 9455 4433 | Email: enquiry@maxworthgroup.com.au