

## CERTIFICATE OF ANALYSIS

(BENTONITE POWDER-API)

Parameter	Protocol	Specification	Result
Viscometer dial reading @ 600 rpm	API 13 A Sec 9	30 MIN	32
Viscometer dial reading @ 300 rpm	API 13 A Sec 9	0	24
Yield point/ plastic viscosity ratio	API 13 A Sec 9	3.0 Max	2
Filtration loss, cc	API 13 A Sec 9	15 cc Max	11.6
Residue of diameter greater than 75 micron	API 13 A Sec 9	4% Max	1.25
Moisture, % wt	UMC/IN/301	11% Max	10.44

**Maxworth International Pty. Ltd.**

Level 1, 76-80 Turnham Avenue, Rosanna Victoria-3084, Australia  
 Tel: +61 3 9455 4400 | Fax: +61 3 9455 4433 | Email: enquiry@maxworthgroup.com.au